

Part Number

Customer

Category	Parameter	Specification	Measurement Method	
OverallWafer	1.0	Diameter	100.00 +/- 0.50 mm	
	2.0	Primary Flat Orientation	{110} +/- 1 degree	Wafer Vendor
	3.0	Primary Flat Length	32.50 +/- 2.50 mm	Wafer Vendor
	4.0	Secondary Flat Orientation	none	
	5.0	Overall Thickness	359.00 +/- 10.00 $\mu$ m	ADE, 100%
	6.0	Total Thickness Variation (TTV)	<3.00 $\mu$ m	
	7.0	Bow	<40.00 $\mu$ m	ADE to ASTM F534, 20%
	8.0	Warp	<40.00 $\mu$ m	ADE to ASTM F657, 20%
	9.0	Edge Chips	0	Bright Light, 100% (note 2)
	10.0	Edge Exclusion	5mm	
HandleSilicon	11.0	Handle Growth Method	CZ	Wafer Vendor
	12.0	Handle Orientation	{100} +/- 1 degree	Wafer Vendor
	13.0	Handle Thickness	350.00 +/- 5.00 $\mu$ m	ADE, 100%
	14.0	Handle Doping Type	N	Wafer Vendor
	15.0	Handle Dopant	Phosphorous	Wafer Vendor
	16.0	Handle Resistivity	1 - 100 Ohmcm	Wafer Vendor
	17.0	Backside Finish	Polished with oxide and lasermark	Wafer Vendor
BuriedOxide	18.0	Oxide Type	Thermal	
	19.0	Oxide Thickness	5,000.00 +/- 250.00 A	Nanospec centre point, 4%
	20.0	Oxide formed on	Handle Wafer	
DeviceSilicon	21.0	Device Growth Method	CZ	Wafer Vendor
	22.0	Device Orientation	{100} +/- 1 degree	Wafer Vendor
	23.0	Nominal Thickness	8.00 +/- 0.50 $\mu$ m	FTIR, 100% 9-Pt (note3 and spec note)
	24.0	Distance to device silicon edge from wafer edge	<= 2mm	Edge defined
	25.0	Device Doping Type	N	Wafer Vendor
	26.0	Device Dopant	Phosphorous	Wafer Vendor
	27.0	Device Resistivity	1 - 100 Ohmcm	Wafer Vendor
	41.0	Voids	none	Wafer Vendor
	42.0	Scratches	0	Bright Light, 100% (note 2)
	43.0	Haze	none	Bright Light, 100% (note 2)
44.0	Device Field Oxidation	5,000.00 +/- 250.00 A	Nanospec 4%, 5pt	

Part Number	Customer
-------------	----------

Category	Parameter	Specification	Measurement Method
----------	-----------	---------------	--------------------


Shipping Details	Wafer per box :	Max 25	
	Packaging :	Taped Polypropylene Wafer Box Empak, Ultrapak, 100.00mm Antistatic Double Bagging	
	Lot Shipment Data	Device Thickness Bow / Warp Data Handle and SOI Thickness	



Explanatory Notes 1. Microscope inspection performed using microscope scan as below. 5x objective.

2. All bright light inspections performed exclude all wafer area outside the edge exclusion defined in Overall Wafer, Edge Exclusion. High intensity bright lamp inspection as per ASTM F523.

3. 9 point measurement are as shown in the diagram below:



Additional Information